

Sheet1

XRF Test Results  
Minserv (Mineral Services)  
5 Cassia Crt, Wantirna VIC 3152

Date: 21 January 2015

Test Time: 30s

Instrument: Moxtek Si Pin

Calculation Method: Fundamental Parameters

Sample: 9K Gold Sheet

Element	Group	Fit Area	Sigma Area	Mass Fraction	wt%
Ni	K	0.00E+000	0.00E+000	0	0
Cu	K	1.25E+005	3.41E+002	0.4388	43.88
Zn	K	2.28E+004	1.66E+002	0.06294	6.29
Ag	K	7.18E+004	2.55E+002	0.1198	11.98
Au	L	1.42E+005	3.68E+002	0.3751	37.51
				0.99664	99.66

