

Sheet1

XRF Test Results
Minserv (Mineral Services)
7 Somerset Court, Leopold, Victoria 3224

Date: 21 January 2017

Test Time: 30s

Instrument: Moxtek Si Pin

Calculation Method: Fundamental Parameters

Sample: Leonora WA Gold Nugget

Element	Group	Fit Area	Sigma Area	Mass Fraction	wt%
Cu	K	0.00E+000	0.00E+000	0	0
Zn	K	0.00E+000	0.00E+000	0	0
Ag	K	2.74E+003	9.10E+000	0.05253	5.25
Au	L	3.36E+004	1.08E+001	0.9469	94.69



