


Sheet1

XRF Test Results  
Minserv (Mineral Services)  
5 Cassia Crt, Wantirna VIC 3152

Client  
Date: 3 Nov 2016  
Test Time: 100s  
Calculation Method: Fundamental Parameters  
Instrument: Moxtek Si Pin  
Sample #: 1

Element	Group	Fit Area	Sigma Area	Mass Fraction	wt%	Major wt%
Cr	K	0.00E+000	0.00E+000	0	0	
Mn	K	0.00E+000	0.00E+000	0	0	
Fe	K	1.03E+002	2.14E+001	0.003476	0.3476	
Co	K	0.00E+000	0.00E+000	0	0	
Ni	K	0.00E+000	0.00E+000	0	0	
Cu	K	5.73E+004	2.32E+002	0.665	66.5	66.5
Zn	K	4.88E+002	2.57E+001	0.004486	0.4486	
Ga	K	1.86E+002	1.76E+001	0.003087	0.3087	
Ge	K	0.00E+000	0.00E+000	0	0	
As	K	1.79E+003	6.52E+001	0.01923	1.923	1.92
Se	K	3.55E+001	1.26E+001	0.0003024	0.03024	
Rb	K	8.63E+001	1.11E+001	0.0004555	0.04555	
Sr	K	1.02E+002	1.07E+001	0.0004607	0.04607	
Y	K	1.72E+002	1.97E+001	0.0006698	0.06698	
Zr	K	7.46E+001	1.22E+001	0.0002745	0.02745	
Nb	K	0.00E+000	0.00E+000	0	0	
Mo	K	0.00E+000	0.00E+000	0	0	
Tc	K	0.00E+000	0.00E+000	0	0	
Ru	K	0.00E+000	0.00E+000	0	0	
Rh	K	0.00E+000	0.00E+000	0	0	
Pd	K	0.00E+000	0.00E+000	0	0	
Ag	K	5.45E+002	3.32E+001	0.001518	0.1518	
Cd	K	5.08E+001	2.52E+001	0.0001645	0.01645	
In	K	0.00E+000	0.00E+000	0	0	
Sn	K	4.92E+004	2.17E+002	0.2462	24.62	24.62
Sb	K	2.29E+003	5.44E+001	0.01542	1.542	1.54
Te	K	6.43E+001	2.66E+001	0.0008268	0.08268	
Pt	L	1.44E+002	2.26E+001	0.001776	0.1776	
Au	L	1.86E+002	1.91E+001	0.002126	0.2126	
Hg	L	2.37E+002	2.07E+001	0.002422	0.2422	
Tl	L	1.34E+002	2.17E+001	0.001213	0.1213	
Pb	L	4.56E+003	8.79E+001	0.03751	3.751	3.75
Bi	L	4.83E+002	2.66E+001	0.003573	0.3573	
Hg	L	1.50E+002	1.26E+001	0.0003258	0.03258	
Tl	L	1.47E+002	1.24E+001	0.0002791	0.02791	
Pb	L	3.23E+002	2.11E+001	0.0005389	0.05389	
Bi	L	1.46E+002	1.29E+001	0.000214	0.0214	



67.63

1.95

25.004

1.57

3.81

